

METALLIC POWDER PIGMENTS



Gold



Bronze



Copper



Russet



Yellow



Silver



Grey



Pearl



Ice White



Black



Red



Blue



Green



Purple



Beige

MIXING GUIDELINES

For Metallic Pigment:

Mix 150g-200g of Metallic Pigment into each 5m² Kit of Design Resin

Metallic Accent Mixing

For creating metallic accents, blend 30-40g of metallic pigment per 1kg of Design Resin (comprising 666g Part A + 333g Part B) - Remember to mix your pigments into the resin Part A thoroughly before mixing in your Part B.


Powder Pigment Mixing :

Allow adequate absorption time when mixing powder pigments into your design resin. After thoroughly blending the pigments for 2-3 minutes, allow a resting period before application. This extended settling time ensures the resin fully penetrates and saturates the pigments, which is especially important when working with higher pigment concentrations (when adding 200g of pigment to a 5m² design kit) - The longer you can wait the better!

PIGMENT PASTES



White Pigment Paste



Black Pigment Paste

USAGE INSTRUCTIONS

Pigment Paste: Use 1 pot (400g) of Pigment Paste per 5m² Kit of Design Resin

For White Paste Only

APPLICATION TIPS

When Installing a floor with a white paste base, consider doubling up your paste to 800g/5m² kit for increased UV Resistance.



Storage Conditions:
Store in cool, dry place

PPE Requirements:



Quality Checks:
Ensure complete dispersion before application